

Roswell Wool

Past Core Results

lbs	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
3541 - 93215							
14,850	1540	20.7	42.3	0.5	82	14	29
2250	1541	21.9					
3362 - 93619							
21,600	1667	21.1	51.2	1.2			
4,950	1668	23.6					
3567 - 95913							
4050	1685	24.9	51.6	0.9	85	21	25
3613 - 95695							
7650	1680	22.3	58.9	1.0	77	14	27
3623 - 95694							
ARMS 5400	1618	24	60.7	0.6	95	13	25
1800	1619	24.1					
3647 - 95432							
2700	1750	26.8					
3073 - 95023							
DIAGNOSTI 6750	1636	27.9					
3214 - 93637							
IAGA 4050	1666	23.5					
3692 - 93635							
19,800	1553	23.2	50.1	1.3			
5400	1554	24.9	53.3	1.1			
4950	1555	23.1					
3600	1556	22.6	50.4	2.6			
2250	1557	21.2					
3600	1660	22.3	53.0	3.7			
3363 - 93619							
40,950	1600	25	53.1	0.6	77	17	32
22,500	1601	25.8	63.6	0.4			
7200	1753	25.9	56.7	3.2			
4500	1754	27.6					
3719 - 95449							
& EXTENS 20,250	1757	22.8	59.7	1.4	77	16	31
3729 - 95830							
	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT

211,050 lb.

Roswell Wool

Past Core Results

lb	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
3020 - 93635							
2250	1662	23.8					
2000	1663	22.6					
3022 - 94512							
4050	1637	22.6	53.0	1.5			
1350	1638	23.3					
3029 - 93210							
13,500	1591	23.6	51.0	0.5			
3600	1592	24.9	60.6	0.3			
3033 - 95669							
3	1760	22.4					
2250							
3038 - 95987							
18,900	1650	23.9	59.6	1.2	75	10	28
4050	1651	23.5					
3064 - 94952							
8550	1777	30.4	58.8	2.8	99	18	32
3067 - 95982							
18,000	1648	21.5	57.6	1.7	74	13	37
1350	1649	20.6					
3081 - 95459							
2700	1772	27.9					
3129 - 95616							
3150	1692	30.8					
3138 - 93656							
5400	1585	25	56.3	0.6			
4050	1586	21	59.5	.5			
28,350	1587	22.6	50	1.1			
4500	1588	22.7	48.2	0.7			
1350	1589	21.5	55.9	0.4			
900	1590	20.8	50.0	0.7			
5850	1627	24.7	59.4	1.7			
3140 - 92596							
5400	1690	21.5	47.7	0.7	81	12	37
3161 - 94952							
	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT

141,500 lb.

Roswell Wool

Past Core Results

16
1800

Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
1646	24.5	58.5	0.9			
3319 - 94571						
9900	23.5	57.4	1.0	84	14	22
2700	26.6					
1800	23.1					
7200	22.8	66.3	1.2			
3329 - 93309						
28,350	21.7	52.2	1.3	71	14	27
6300	19.3	57.0	1.2			
3566 - 83347						
1154	25.3	61.1	0.8	76	10	30
1155.1	21.7	60.1	1.0			
1156.1	25.1	57.2	1.4			
1157.1	24.5	56.5	0.9			
1158	28	64.0	0.8			
1674	23.4	56.2	0.5			
1675	26					
3435 - 95937						
4050	24.9	51.6	0.9	85	21	25
3220 - 95620						
16,200	22.3	46.6	1.8	73	18	30
2250	22.1					
22,050	21.4	59.6	1.2	89	14	34
2700	23.8					
8550	25.1	59.4	1.7			
3476 - 95953						
23,400	22.3	57.4	0.8	80	19	34
1800	21.3					
3483 - 96119						
11,700	26.2	51.4	0.9	80	14	26
8,100	29.2					
3514 - 93446						
3150	23.2	52.0	2.2	80	10	24
3518 - 90049						
3150	21.4	50.8	1.0	83	11	25

165,150 16

Roswell Wool

Past Core Results

Weight	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
<u>165</u> 2250	1547	23.5					
	3348 - 95913						
5400	1677	24.3	59.8	0.4	98	15	38
3600	1678	23.3					
2250	1679	26.4					
	3359 - 93561						
3150	1676	25					
	3360 - 93388						
12,600	1582	22.1	46.3	1.9	78	17	29
1800	1583	22.3					
	3373 - 94971						
9000	1768	32.9	56.9	0.7			
	3389 - 95249						
2250	1760	22.4					
	3415 - 96101						
11,700	1652	24.3	57.0	0.8	80	14	40
6300	1653	21	56.0	0.9	78	14	38
	3416 - 93637						
26,700	1560	23	49.1	1.1	87	21	29
7650	1661	23.3	58.2	1.1			
	3449 - 94952						
8100	1778	30.5	55.2	2.0	107	24	34
	3450 - 93307						
31,500	1576	21.7	47.7	1.4	78	20	27
6300	1578	22.1	47.1	2.0	86	23	22
	3468 - 94571						
6300	1608	24.2	60.8	1.8	80	13	31
4500	1609	27.1	63.9	1.3	86	15	27
6300	1610	22.9					
31,050	1611	21.5					
5400	1641	25.3					
	3466 - 94571						
2250	1622	22.4					
2250	1623	23.9					
4950	1624	22	58.1	1.3	74	13	23

203,550 lb.

Roswell Wool

Past Core Results

	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
<u>1b</u>	3508 - 95620						
4050	1620	26.5					
6300	1621	25.5	60.8	2.5	83	11	26
	3515 - 92509						
12,150	1756	21.9	41.1	3.4	72	16	23
	3560 - 94585						
1350	1647	24.9					
	3580 - 94950						
13,050	1759	31.3	63.8	0.4	100	23	31
	3655 - 95698						
7650	1680	22.3	58.9	1.0	77	14	27
900	1681	21.5					
	3686 - 95377						
10,800	1531	22.4	54.8	2.4	79	14	24
4950	1532	25.7	58.8	3.0	86	13	31
2700	1533	23.3					
3150	1534	23.4					
2250	1535	26.7					
	3668 - 95558						
1800	1765	34.9					
	3628 - 94952						
3150	1769	29.1	54.7	0.9			
	3697 - 95966						
4050 ¹	1956.3	23.6	49.9	3.7			
	3735 - 93451						
3150	1676	25					
	3757 - 94585						
3150	1644	21.9	58.2	2.0			
	3771 - 95616						
3150	1692	30.8					
	3774 - 93635						
A 5850	1781	23.9	50.6	1.6			
	3037 - 95204						
NC. 1800	1656	25.4	57.6	1.7			

95,400 lb.

Roswell Wool

Past Core Results

	Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
1b 1350 3600	1657 3124 - 93407 1770	27.4 28.3	63.8	0.9			
41,850 11,250	3759 - 93210 1612 1614	22.9 24.3	50.1 60.7	0.5 0.4	73	10	22
24,300 5850 4500 3600 1800 900 7200 1800	3025 - 94512 1602 1603 1604 1605 1606 1607 1642 1643	24.2 22.2 26.2 23.7 24.5 22.5 26.5 22.8	54.0 61.5	2.3 1.6	81 79	14 10	29 29
42,300	3215 - 93380 1564	23.2	46.6	0.5	75	14	33
13,050 2250 4050 900	3219 - 94571 1631 1632 1639 1640	22 21.3 21 21.6	60.7	1.5	77	11	27
20,250 1800 6300 6300	3232 - 93314 1596 1597 1598 1599	22.4 24.6 20.5 22.4	46.8 49.2 45.9	0.8 1.7 0.7			
34,200 11,700 3150	3237 - 93312 1584 1594 1676	22.8 22.5 25	54.3 54.9	0.7 0.9			
4500	3269 - 92582 1673	23.5	47.7	0.9	87	15	28
3150	3273 - 94512 1645	27.5					

261,900 lb.

Roswell Wool

Past Core Results

165
1800
1350

Lot Number	Fiber Diameter:	Yield	V M	MM-	CV-	N/KT
1775		34.2				
1776		32.5				
3169 - 95404						
4050 Lot Number 1758	Fiber Diameter:	31.1				
3210 - 93388						
9450 Lot Number 1538	Fiber Diameter:	22.1	Yield 50.5	V M 0.3	MM- 71	CV- 17
3211 - 93622						
18,900 Lot Number 1566	Fiber Diameter:	22.5	Yield 50.2	V M 1.7	MM- 76	CV- 14
12,600 Lot Number 1567	Fiber Diameter:	22.5	Yield 49.5	V M 1.0	MM- 70	CV- 13
4500 Lot Number 1568	Fiber Diameter:	23.5	Yield 53.3	V M 0.7		
2250 Lot Number 1569	Fiber Diameter:	22.4				
3216 - 93637						
13,500 Lot Number 1523	Fiber Diameter:	24.1	Yield 53.4	V M 1.0	MM- 77	CV- 13
5400 Lot Number 1524	Fiber Diameter:	23.1	Yield 52.9	V M 1.3		
3150 Lot Number 1525	Fiber Diameter:	27.2				
1800 Lot Number 1664	Fiber Diameter:	22.3				
3217 - 93637						
11,250 Lot Number 1526	Fiber Diameter:	23.5	Yield 52.3	V M 1.0	MM- 81	CV- 11
5850 Lot Number 1527	Fiber Diameter:	23.2	Yield 52.1	V M 1.2	MM- 74	CV- 19
1800 Lot Number 1528	Fiber Diameter:	27				
900 Lot Number 1665	Fiber Diameter:	22				
3231 - 93308						
14,400 Lot Number 1593	Fiber Diameter:	23.1	Yield 46.2	V M 0.7	MM- 88	CV- 24
3233 - 93245						
12,150 Lot Number 1751	Fiber Diameter:	22.7	Yield 52.1	V M 1.4		
11,700 Lot Number 1752	Fiber Diameter:	25.4	Yield 54.1	V M 1.7		
3252 - 95648						
1800 Lot Number 1691	Fiber Diameter:	29.5		V M	MM-	CV-
3281 - 95963						
1800 Lot Number 1699	Fiber Diameter:	22.7		V M	MM-	CV-
3293 - 94952						
4950 Lot Number 1767	Fiber Diameter:	33.2	Yield 67.6	V M 1.3		
3304 - 93313						
25,650 Lot Number 1543	Fiber Diameter:	20.7	Yield 45.4	V M 0.5	MM- 78	CV- 15
3150 Lot Number 1546	Fiber Diameter:	19.6	Yield 51.6	V M .5		

174,150 lb

Roswell Wool

Past Core Results

lbs	CO.	Lot Number	Fiber Diameter:	Yield	VM	MM-	CV-	N/KT
1694			24.3	55.3	0.8	85	17	20
7200								
2700			1695	23.6				
	3721	- 95825						
3400		1683	21.4	56.6	1.8	75	12	20
2250		1684	21.5					
	3336	- 95468						
4500		1766	33.1					
	3773	- 93635						
20,250		1686	22.2	54.2	1.0	86	12	32

+ APPX 255,000? Bakersfield, CA area 21-22 micron 75mm

295,500

1,548,200 lbs Cored CA wool 2012